

## **OAK MARKANT / 15 MM**

## CHARAC-TERISTICS

O Tongue and groove all round, mini bevel all round, surface sanded with 150 grit, in accordance with EN standard 13629

- O Standard finish: 2 x natural oiled
- O Fixed lengths: 1753 mm, 2053 mm, 2653 mm
- O FSC on request
- O Wood moisture 9 % +/- 2%



Thickness♥ Width ▶	3	1	-		₩	å	137 mm	168 mm	Pcs./package
15 mm	•		•	•		•	•		8
15 mm			•	••				•	8

suitable installation;
 standard programme

Packing: 8 pcs./package

**DiBt:** building authority approval

Cracks: Occasional surface cracks are permi ssible (filled). Hairline cracks are occasionally permitted. Head cracks are permissible when filled with putty.

Bark pockets: Occasional bark pockets up to a size of 2 cm² are permissible.

**Knots:** Sound knots are permissible in any number up to a maximum size of half a board width. Cracks in the knots are fillered. Dark knots up to a size of 25 mm are permissible. Small knot cracks

and edge chipping are occasionally permissible. Loose or falling knots are not permissible. **Discolouration:** natural discolouration and vivid structure are permissible.

Sapwood: Sapwood at the edge up to 1/10 of the board width is permissible

Wood growth: different grain patterns are permissible.

**Pith ray:** a light pith ray with a maximum of half the board length is permissible for a maximum of 20 % of the number of pieces.

Pest infestation: Not permissible

## Extract from standard EN 13629\_2012 (D)

Maximum deviation from nominal dimensions of the element at the time of initial delivery. Based on a reference wood moisture content of 9 %. Valid for planks with raw sanded surface.

Length: ± 2,0 mm
Thickness: + 1.0 mm

Longitudinal curvature horizontal up to 1 m: 0,5 % based on total length Longitudinal curvature horizontal from 1 m: 2 % based on total length

Width: ± 1.0 mm

Transverse curvature:  $\leq$  0,7 %

Offset: ≤ 0,3 mm

Perpendicularity: Max. 0,2 % of the plank width

Longitudinal curvature horizontal when glued: 1 ‰ based on total length

Longitudinal curvature vertical: 0,5 % related to length

No. FW85510500: Surface oil-Kneho | Bending resistant floor elements - components wood flooring system 3 | EPH Desden -TPC No. W-12-010 | EN 14342 : 2013 No. FW85510001: Surface unfinished | Bending resistant floor elements - components wooden flooring system 4 | EN 14342 : 2013 EN 2013 No. FW85510200: Surface lacquer-Kneho | Bending-resistant floor elements - components wooden flooring system 4 | EN 14342 : 2013 Main features Cfl,-s1 spruce, beech, oak Behaviour in fire Dfl,-s1 other wood species Emission (content) of formaldehyde PCP < 5 x 10-6n Emission of (content of) pentachlorophenol EN 14342:2013 no performance requirement defined Emission of other dangerous substances Breaking strength, sliding resistance, thermal conductivity no performance requirement defined according to EN 335 Natural durability against fungal infestation Technical characteristics Thermal resistance m<sup>2</sup>K/W =0,09 Lambda value (thermal conductivity) λ-value = 0,17



## THE INSTALLATION OPTIONS:



Floating installation with clips 135/137 mm plank width



Installation with glue



Dry construction elements with underfloor heating (screwed to intermediate battens)



Installation with screws



Full-surface bonding on underfloor heating



Installation with clips on underfloor heating (screed or dry construction systems; floating "System FEEL WOOD")

Type of wood	λ-Value	m²K/W	Thickness [mm]	Width [mm]	এ	/	<i>'''!!</i> !	<u></u>	<b>=</b>	<u>#</u>
Spruce	0,13	0,12	15	135	•		•	•		0
Spruce	0,13	0,15	19	135	•	•	•	0	•	0
Spruce	0,13	0,19	25	135	•	•	•			
Pine	0,13	0,15	19	135	•	•	•	0	•	0
Larch Siberian	0,15	0,10	15	135	•		•	•	•	•
Larch Siberian	0,15	0,13	19	135	•	•	•	0	•	0
Larch Siberian	0,15	0,13	19	178		•	•			
Larch Siberian	0,15	0,17	25	135	•	•	•			
Larch Siberian	0,15	0,17	25	178		•	•			
Larch European	0,12	0,16	19	135	•	•	•			
Stone pine	0,13	0,15	19	135	•	•	•	0	•	0
Oak	0,17	0,09	15	137	•		•	•		•
Oak	0,17	0,09	15	168			•	••		
Oak	0,17	0,12	21	137	•	•	•	•	•	•
Oak	0,17	0,12	21	168		•	•	••	••	
Oak	0,17	0,12	21	198		•	•			
Oak	0,17	0,16	27	188		•	•			
Ash	0,17	0,12	21	137	•	•	•	•	•	•

Glue (e.g. Sika 54)	0,08	0,03	2
Cork	0,08	0,04	3
Wood fibre board	0,07	0,04	3

 $\begin{array}{l} m^2 K/W \\ \lambda \text{-Value} \end{array}$ 

thermal resistance

Lambda value (thermal conductivity)

- suitable installation method
- •• suitable for underfloor heating; in case of deviations of the room climate outside the optimal range joint formation or cupping to a small extent is to be expected.
- conditionally suitable for underfloor heating; depending on additionally used system elements, the recommended thermal resistance could be exceeded. Slower reaction time during heating/cooling is to be expected!